



# Strip-N-Flash™

Specification Bulletin

No. 105

Strip-N-Flash™

## Strip-N-Flash® | Self Adhering Cavity Wall Membrane

### DESCRIPTION:

Strip-N-Flash® is a 40 mil. thick membrane consisting of a 32 mil. self-adhering rubberized asphalt laminated to an 8 mil. high density polyethylene film. A siliconized release liner prevents the product from sticking to itself in the roll. The factory-controlled quality assures uniform thickness on the job and the name Strip-N-Flash® assures an excellent water barrier.

### TYPICAL USE:

Strip-N-Flash® thru-wall membrane is designed to provide moisture protection in a cavity wall application. Its self-adhesive nature allows easy installation on concrete, masonry, gypsum, steel and wood substrates.

### PACKAGING:

- 12" x 75' (75 sq ft), 3 rolls per box
- 16" x 75' (100 sq ft), 2 rolls per box
- 18" x 75' (112.5 sq ft), 2 rolls per box
- 24" x 75' (150 sq ft), 1 roll per box
- 36" x 75' (225 sq ft), 1 roll per box.

Use water based primer as required.

### ADVANTAGES:

- » The inherent durability of the extra strength 8 mil. cross-laminated polyethylene film resists mechanical damage and ensures the integrity of the rubberized asphalt waterproofing membrane during subsequent wall construction.
- » Strip-N-Flash® provides a waterproof barrier at flashing areas to prevent wall assembly leaks.
- » Strip-N-Flash® is fully adhered to the substrate to prevent moisture migration behind the flashing.
- » The unique rubberized nature of Strip-N-Flash® seals around fasteners.

### LIMITATIONS:

- » Not recommended in areas where membrane will be subject to continuous sunlight or temperatures in excess of 180°F.
- » Do not apply primer or membrane to frozen substrates. Best results are obtained when membrane is installed at temperatures above 40°F.
- » Do not apply primer or membrane to damp or contaminated surfaces.
- » Not recommended for use with sealants containing coal tar or polysulfides.
- » UV Exposure Limited to 30 Days.



**ADVANCED BUILDING PRODUCTS, INC.**  
Phone: 800-252-2306 Fax: 207-490-2998  
info@abp-1.com www.advancedbuildingproducts.com



REV. 09/19

TECHNICAL DATA		
PROPERTY	ASTM	RESULTS
Thickness		40 mils
Tensile Strength	D-412	1200 psi. min
Elongation	D-412	200% min.
Pliability	D-146	Pass @ -25°F 1/4" mandrel
Peel Adhesion	D-903	5-lbs./in. min.
Puncture Resistance	E-154	40 lbs. min

% of elongation to ultimate failure of rubberized asphalt membrane.

## INSTALLATION:

- » **Surface Preparation:** Concrete shall be in place for 7 days minimum. Substrate must be completely dry. Surface shall have a smooth finish free of voids, sharp protrusions, laitance and form release agents. Block or brick walls shall have mortar joints struck flush.
- » **Primer:** Surfaces to receive Strip-N-Flash® must be clean and dry. For best results, concrete, masonry and some exterior gypsum substrates require coating with Primer. Apply Primer per manufacturer's recommendations. **Warning:** Avoid breathing vapors from the primer. Use in areas with adequate ventilation. Refer to SDS for important warnings and safety information.
- » **Application:** Precut Strip-N-Flash® to fit each location. Remove siliconized release liner and position membrane carefully before pressing in place. Press firmly in place with a steel hand roller, taking care to avoid air pockets and wrinkles. Overlap adjoining pieces 2 inches. Cut bottom edge back 1/2 inch from exterior surface of building and place on drip edge. Be sure Strip-N-Flash® is installed a minimum of four-inches above the mortar deflection.
- » **Terminations:** Press termination edges firmly in place with a hammer handle or similar tool. The use of a surface mounted termination bar or placing the flashing membrane into a joint of the inner back up wall is recommended for vertical terminations. ABP End Dams are recommended at horizontal terminations. **Note:** Failure to use adequate pressure at terminating edges will result in a poor seal and a potential leak.

## STORAGE:

Store material in an area where temperature does not exceed 90°F or below 40°F. Store material away from open flame, sparks, or welding. For outside storage, protect material from direct sunlight or other harmful environment conditions.

## STRIP-N-FLASH™ ACCESSORIES

### TERMINATION BARS

#### Stainless Steel Termination Bars:

.100" thick, 1" X 8'. Holes are 8" on center.

#### Aluminum Termination Bars:

(Alloy 6063) .090" thick, 1" X 10'. Holes are 8" on center.

#### Plastic Termination Bars:

.125" thick, 1" x 8'. Can be custom cut to size and easily fastened on the job site.



### PRIMER & MASTIC

- High quality, trowel grade, water based rubberized bitumen mastic that dries to a pliable seal allowing for minor expansion & contraction. Available in 10.5 oz. tubes, quart tubes, and 3 gallon buckets.

- For multiple uses, including finishing the edge of seams, overlaps, patches and terminations of properly sealed waterproofing membranes. Applied with a trowel or caulking gun.

- Suitable for use in roof flashing application and contains additives for use in wet and dry conditions. 5-year Limited Warranty and Arbitration Agreement.

**For more information on our primer, call 800-252-2306**

